



Product Specifications

RPO 702 (AROMATIC)

RPO, both synthetic and natural are commercially used to produce products from rubber bands to a toy to the gaint tyres for various vehicles including aircrafts.

Parameters	Method	Unit	Typical Result
Anniline	ASTM D116	°C	35 - 55
Color	ASTM D1500	-	Greenish
Density	ASTM D1298	Kg/L	1.022
Viscosity @ 40 °C	ASTM D445	cSt	8_12
Flash Point	ASTM D92	°C	201
Pour Point	ASTM D97	oC	21
Water Content	ASTM D95	% Vol	nil
Sulfur	ASTM D4294	Wt %	1.19

